

Aggregate Optimization Chart

MIX ID'S: DDD0K7E7, DDD0K7E8 and DDD0K7E9

Production Gradation Report

PLANT #: **P-102**

Sample Date: 4/2/18

Concrete Grade: **DM**

Contractor: _____

Dates Test Represents: 4/2/2018 to 4/9/2018

MDOT No.: _____

Agg. Class	Pit #	Source	Weight (SSD)	ft ³	Specific Gravity	% Contribution
6AA	58-003	Stoneco	1495	8.91	2.69	49.9
26A	58-003	Stoneco	300	1.79	2.69	10.0
2NS	47-16	Buno Road	1200	7.26	2.65	40.1
Total Wt			2995	17.95		100.0

<----- Verify this number is 100%




Superior Materials, LLC
 30701 W. 10 Mile Rd.
 Suite 500
 Farmington Hills, MI 48336

Sieve	6AA	26A	2NS	Cumulative % Passing	% Retained	Cumulative % Retained
2"	100.0	100.0	100.0	100.0	0.0	0.0
1.5"	100.0	100.0	100.0	100.0	0.0	0.0
1"	99.5	100.0	100.0	99.8	0.2	0.2
3/4"	77.9	100.0	100.0	89.0	10.8	11.0
1/2"	41.2	99.8	100.0	70.6	18.3	29.4
3/8"	23.0	89.0	100.0	60.5	10.2	39.5
#4	5.6	23.4	96.1	43.6	16.8	56.4
#8	3.2	6.2	86.1	36.7	6.9	63.3
#16	1.6	2.6	72.7	30.2	6.5	69.8
#30	1.5	1.8	53.5	22.4	7.8	77.6
#50	1.4	1.6	19.9	8.8	13.5	91.2
#100	1.3	1.5	3.0	2.0	6.8	98.0
LBW	1.6	1.4	0.5	1.1	0.9	98.9

*Maximum % Retained must be above the 3/8" sieve.
 *Any two adjacent sieves must equal 10% except max., nom. max., #100 and #200 sieves.
 *% Retained must be at least 4% for each sieve except max., nom. max., #100 and #200 sieves.
 *% Retained must be at least 8% for the 1" sieve when a 2" max. size (nom. Max. 1.5") aggregate is used.

Production Gradation Batch Plant Gradations Aggregate Supplier Gradations

Coarseness Factor:	62	Workability Factor:	37
---------------------------	-----------	----------------------------	-----------



Initial Production Sample (IPS)

Sieve	Cumulative % Passing	% Retained	Cumulative % Retained
2"	100.0	0.0	0.0
1.5"	100.0	0.0	0.0
1"	99.3	0.7	0.7
3/4"	89.2	10.1	10.8
1/2"	70.7	18.5	29.3
3/8"	60.7	10.0	39.3
#4	44.4	16.3	55.6
#8	35.9	8.5	64.1
#16	27.3	8.6	72.7
#30	19.1	8.2	80.9
#50	7.4	11.7	92.6
#100	1.9	5.6	98.1
LBW	0.7	1.2	99.3

PREPARED BY:

Approved By: