

Aggregate Optimization Chart

MIX ID'S: DDP154E7 and DDP154E8

Production Gradation Report

PLANT #: **P-102**

Sample Date: 8/7/17

Concrete Grade: **P1M**

Contractor: _____

Dates Test Represents: 8/7/2017

8/13/2017

MDOT No.: _____

Agg. Class	Pit #	Source	Weight (SSD)	ft ³	Specific Gravity	% Contribution
CA	58-003	Stoneco	1320	7.86	2.69	41.9
IA	58-003	Stoneco	600	3.57	2.69	19.0
2NS	63-114	AA Highland	1230	7.44	2.65	39.0
Total Wt			3150	18.88		100.0

<----- Verify this number is 100%




Superior Materials, LLC
 30701 W. 10 Mile Rd.
 Suite 500
 Farmington Hills, MI 48336

Sieve	CA	IA	2NS	Cumulative % Passing	% Retained	Cumulative % Retained
2"	100.0	100.0	100.0	100.0	0.0	0.0
1.5"	100.0	100.0	100.0	100.0	0.0	0.0
1"	62.4	100.0	100.0	84.2	15.8	15.8
3/4"	35.8	100.0	100.0	73.1	11.1	26.9
1/2"	10.7	90.8	100.0	60.8	12.3	39.2
3/8"	4.8	82.8	100.0	56.8	4.0	43.2
#4	1.9	25.6	99.8	44.6	12.2	55.4
#8	1.6	5.9	89.1	36.6	8.1	63.4
#16	1.4	2.1	67.9	27.5	9.1	72.5
#30	1.3	1.4	46.4	18.9	8.6	81.1
#50	1.2	1.2	17.3	7.5	11.4	92.5
#100	1.2	1.2	2.4	1.7	5.8	98.3
LBW	1.1	1.0	0.3	0.8	0.9	99.2

*Maximum % Retained must be above the 3/8" sieve.
 *Any two adjacent sieves must equal 10% except max., nom. max., #100 and #200 sieves.
 *% Retained must be at least 4% for each sieve except max., nom. max., #100 and #200 sieves.
 *% Retained must be at least 8% for the 1" sieve when a 2" max. size (nom. Max. 1.5") aggregate is used.

Production Gradation Batch Plant Gradations Aggregate Supplier Gradations

Coarseness Factor: **68** Workability Factor: **37**



Initial Production Sample (IPS)

Coarseness Factor: 67		Workability Factor: 36	
Sieve	Cumulative % Passing	% Retained	Cumulative % Retained
2"	100.0	0.0	0.0
1.5"	100.0	0.0	0.0
1"	87.2	12.8	12.8
3/4"	76.6	10.6	23.4
1/2"	64.4	12.2	35.6
3/8"	56.9	7.6	43.1
#4	44.1	12.7	55.9
#8	35.6	8.5	64.4
#16	27.7	8.0	72.3
#30	19.5	8.2	80.5
#50	7.8	11.6	92.2
#100	2.3	5.6	97.7
LBW	0.6	1.6	99.4

PREPARED BY:

Approved By: